

Akulon® F130-C2

PA6

Medium Viscosity, Film Extrusion, Lubricated, Food Contact Quality

Print Date: 2024-03-27

| PROPERTIES | TYPICAL DATA | UNIT | TEST METHOD |
|--|--------------|----------|-------------------------------|
| MATERIAL SPECIFIC PROPERTIES | VALUE | | |
| Viscosity number | 196 | cm³/g | ISO 307, 1157, 1628 |
| RSV formic acid, 1g/100ml | 3.03 | _ | Envalior Method |
| Melt Viscosity (260 °C) | 810 | Pa s | Envalior Method, 260°C |
| Density | 1130 | kg/m³ | ISO 1183 |
| THERMAL PROPERTIES | VALUE | | |
| Coeff. of linear therm. expansion (parallel) | 0.9 | E-4/°C | ISO 11359-1/-2 |
| Spec. heat capacity | 1550 | J/(kg K) | _ |
| Average spec. heat capacity 20–150 °C | 2250 | J/(kg K) | |
| MECHANICAL PROPERTIES (FILM) | VALUE | | |
| Modulus of elasticity | 455 | MPa | Envalior Method, 50 mm/min |
| Stress at yield, parallel | 31 | MPa | ISO 527-3 |
| Maximum stress, parallel | 82 | MPa | ISO 527-3 |
| Maximum strain, parallel | 350 | % | ISO 527-3 |
| Trouser Tear resistance, parallel | 32 | _ | ISO 6383-1 |
| Puncture resistance | 1300 | J/m | Envalior Method |
| Static coefficient of friction | 1.2 | _ | ISO 8295 |
| Dynamic coefficient of friction | 1 | _ | ISO 8295 |

OTHER PROPERTIES (FILM)

VALUE

All the trademarks mentioned here are trademarks of Envalion

All the trademarks mentioned here are trademarks of Envalior. Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.


Property Data

Akulon® F130-C2

Print Date: 2024-03-27

| PROPERTIES | TYPICAL DATA | UNIT | TEST METHOD |
|---|--------------|----------------|-----------------|
| Transparency/Clarity | 83 | % | Envalior Method |
| Oxygen transmission rate at 23°C/0%r.h. | 26 | cm³/(m²*d*bar) | DIS 15105-1/-2 |
| Oxygen transmission rate at 23°C/85%r.h. | 38 | cm³/(m²*d*bar) | DIS 15105-1/-2 |
| Water Vapor Transmission Rate at 23°C/85%r.h. | 35 | g/(m²*d) | DIS 15106-1/-3 |
| | | | |
| TEST SPECIMEN PRODUCTION (FILM) | VALUE | | |
| Type of extrusion | cast | _ | |
| Thickness of specimen | 0.05 | mm | _ |
| Extruder temperature | 270 | °C | |
| Die temperature | 270 | °C | |
| Chill Roll Temperature | 110 | °C | |

Viscosity-shear rate



All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.