

Akulon[®] K225–KV

PA6 FR(30)

Flame Retardant (halogen free), Heat Stabilized

Print Date: 2024–03–27

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	1 / *	%	ISO 294–4
Molding shrinkage (normal)	1 / *	%	ISO 294–4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	4200 / 1600	MPa	ISO 527–1/–2
Nominal strain at break	4 / >50	%	ISO 527–1/–2
Yield stress	70 / 35	MPa	ISO 527–1/–2
Yield strain	3 / 30	%	ISO 527–1/–2
Charpy impact strength (+23°C)	40 / –	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4 / 9	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (–30°C)	3 / 5	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357–1/–3
Burning Behav. at 1.5 mm nom. thickn.	V–2 / *	class	IEC 60695–11–10
Thickness tested	1.5 / *	mm	IEC 60695–11–10
Burning Behav. at 3.0 mm nom. thickn.	V–2 / *	class	IEC 60695–11–10
Thickness tested	3 / *	mm	IEC 60695–11–10
Burning Behav. at 0.4 mm nom. thickn.	V–2 / *	class	IEC 60695–11–10
Thickness tested	0.4 / *	mm	IEC 60695–11–10
Burning Behav. at 0.75 mm nom. thickn.	V–2 / *	class	IEC 60695–11–10
Thickness tested	0.75 / *	mm	IEC 60695–11–10
Glow Wire Flammability Index GWFI	960 / –	°C	IEC 60695–2–12

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

Property Data

Akulon[®] K225–KV

Print Date: 2024–03–27

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
GWFI (Thickness (1) tested)	0.38 / –	mm	IEC 60695–2–12
Glow Wire Flammability Index GWFI	960 / –	°C	IEC 60695–2–12
GWFI (Thickness (2) tested)	3 / –	mm	IEC 60695–2–12
Glow Wire Ignition Temperature GWIT	930 / –	°C	IEC 60695–2–13
GWIT (Thickness (1) tested)	0.38 / –	mm	IEC 60695–2–13
Glow Wire Ignition Temperature GWIT	850 / –	°C	IEC 60695–2–13
GWIT (Thickness (2) tested)	3 / –	mm	IEC 60695–2–13

ELECTRICAL PROPERTIES

DRY / COND

Relative permittivity (100Hz)	3.3 / 8	–	IEC 62631–2–1
Relative permittivity (1 MHz)	3.2 / 3.6	–	IEC 62631–2–1
Dissipation factor (100 Hz)	90 / 1250	E–4	IEC 62631–2–1
Dissipation factor (1 MHz)	200 / 800	E–4	IEC 62631–2–1
Volume resistivity	>1E13 / 1E11	Ohm*m	IEC 62631–3–1
Surface resistivity	– / 1E14	Ohm	IEC 62631–3–2
Electric strength	30 / 25	kV/mm	IEC 60243–1
Comparative tracking index	600 / –	V	IEC 60112

OTHER PROPERTIES

DRY / COND

Water absorption	7.5 / *	%	Sim. to ISO 62
Humidity absorption	2 / *	%	Sim. to ISO 62
Density	1210 / –	kg/m ³	ISO 1183

All the trademarks mentioned here are trademarks of Envalior.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.

Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.