**Property Data** 



# Stanyl<sup>®</sup> TC155

### **PA\* FR(17)**

Thermal conductive material, Flame Retardant, Heat Stabilized

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	DRY / COND		
Molding shrinkage [parallel]	0.3 / *	%	Sim. to ISO 294–4
Molding shrinkage [normal]	0.3 / *	%	Sim. to ISO 294–4
MECHANICAL PROPERTIES	DRY / COND		
Tensile modulus	11000 / -	MPa	ISO 527-1/-2
Stress at break	55 / -	MPa	ISO 527-1/-2
Strain at break	0.6 / -	%	ISO 527-1/-2
Charpy impact strength (+23°C)	10 / -	kJ∕m²	ISO 179/1eU
Charpy impact strength (-30°C)	10 / -	kJ∕m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	2/-	kJ∕m²	ISO 179/1eA
Charpy notched impact strength (-30°C)	1.6 / -	kJ∕m²	ISO 179/1eA
THERMAL PROPERTIES	DRY / COND		
Coeff. of linear therm. expansion (parallel)	0.25 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.25 / *	E-4/°C	ISO 11359-1/-2
Thermal conductivity in plane	5	W/(m K)	ASTM E1461
Thermal conductivity through plane	1	W/(m K)	ASTM E1461
Burning Behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	_	_
Burning Behav. at 3.0 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	3/*	mm	IEC 60695-11-10
UL recognition	Yes / *	_	

#### Print Date: 2024-03-27

All the trademarks mentioned here are trademarks of Envalion

All the trademarks mentioned here are trademarks of Envalior. Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied. In that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

## **Property Data** Stanyl<sup>®</sup> TC155

#### Print Date: 2024-03-27

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
ELECTRICAL PROPERTIES	DRY / COND		
Comparative tracking index	575 / -	V	IEC 60112
Relative permittivity (10GHz)	3.89 / -	_	IEC 61189-2-721
OTHER PROPERTIES	DRY / COND		
Density	1620 / -	kg∕m³	ISO 1183

All the trademarks mentioned here are trademarks of Envalior. Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.